resina color
made in italy
painting the difference

Scheda Tecnica

MUROVIVO

Water-soluble anti-mould paint

Anti-condensation paint

Breathable paint

Code	0824
Description	Resin-based paint modified with hollow glass beads, to ensure a good thermal insulation and to avoid the formation of condensation.
Use	Suitable for the protection of wall surfaces in humid or condensed environments such as: bathrooms, kitchens, cellars, laundries, etc. It can be applied on old and new plasters, on concrete, plaster and plasterboard surfaces and old paints as long as they are very tight.
Appearance of the film	Matt
Color	White and colour chart
Component	1
Hardening	Physical by evaporation of water and coalescence of the polymer.

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729
www.resinacolor.com - www.resinacolor.it

Specific weight	Da 0,900 gr/ml
VOC	12 gr/ liter
Estimated yield	6 m^2/ L for smooth medium absorption surfaces
Flash point	Component A > 114°C
Preparation of surfaces	New surfaces: New plasters must be seasoned, cleaned and dried. In case of mould, treat the surface with suitable healing. Remove any efflorescence by brushing or washing. Prime clean surfaces with acrylic fixatives. Already painted surfaces: Remove the detaching parts. In case of tempera or lime based paints, provide for the total removal by washing and brushing.
Preparation of the product	Mix the product before use and add water Component A 100 Water max. 5 – 10 %
Environmental conditions	Ambient temperature: from + 8 to 40°C Temperature of the surface: > 10°C Humidity: 0 – 80 % To prevent the formation of condensation, the temperature of the surface must be at least 3 ° C higher than the dew point.
Warnings:	Do not apply the product to wet or unseasoned surfaces Do not apply the product at temperatures below 10 °c Do not apply the product with specific humidity above 80%.

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729
www.resinacolor.com - www.resinacolor.it

Drying and hardening times	For thicknesses of 100 microns 10°C 20°C 30°C Dry to the touch 3 1 0,5 hrs Dry in depth 12 8 4

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729
www.resinacolor.com - www.resinacolor.it

Time for overpainting	Minimum: (hrs) 10°C 20°C 30°C 12 8 4 Maximum: unlimited, except for the presence of contaminants on the surface
Application	Brush and paint roller For brush applications use nylon or pure bristle brushes. For roller applications use medium-hair rollers. For the application use the method of the crossed hands
Shelf life	2 years in a cool and dry place (max 40 ° C)
Packs	Comp A

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729
www.resinacolor.com - www.resinacolor.it